

Silicon Powder 0-0,070mm/ 0-0,200mm

Main application:

- Refractory industry
- Chemical Industry
- Ceramic and carbon sinter products

Chemical composition:

Si	> 98,0 %
Fe	ca. 0,6 %
Al	ca. 0,5 %
Ca	ca. 0,2 %
Ti	ca. 0,1 %

Screen analysis:

0-0,070 mm

> μ71	Max. 10 %
--------------------------------	------------------

0-0,200 mm

Si	>97,5 %
Fe	ca. 0,7 %
Al	ca. 0,6 %
Ca	ca. 1,0 %
Ti	ca. 0,1 %

> 0,5 mm	0,2 %
> 0,2 mm	0,5 %
> 0,1 mm	4,0 %
> 0,08 mm	7,0 %
> 0,05 mm	20,0 %
> 0,02 mm	50,0 %
< 0,02 mm	18,3 %

Size distribution, other elemental composition and trace elements can be individually agreed

Packing:

Big Bags on pallets

Seller/ Producer:

PCC BakkiSilicon hf
Bakkavegur 2
IS-640 Húsavík
Iceland
Internet: www.pcc.is

Contact sales:

Mr. Rolf Prack
Tel.: +49 [0] 2066 2019 37
Email: rolf.prack@pcc.eu